

1734

RECEIVED
CENTRAL FAX CENTER

NOV 08 2007

AMENDMENTS TO THE CLAIMS

The listing below of the claims will replace all prior versions and listings of claims in the present application:

Listing of Claims:

Claim 1 (currently amended): A method of producing a molybdenum-silicide- type based heating element containing essentially molybdenum silicide and alloys of that material, said method comprising the steps of: producing a heating element material that contains substantially $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 by mixing a molybdenum aluminum silicide $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$ with SiO_2 , wherein the SiO_2 replaces bentonite clay in molybdenum silicide heating element compositions containing bentonite clay and is at least 98% pure, and wherein x lies in the range of 0.4 - 0.6; and forming a heating element from the produced material, wherein the heating element includes on its surface ~~a protective~~ an oxide layer consisting essentially of Al_2O_3 that , which oxide layer does not peel from the surface of the heating element under thermal cycling of the heating element between room temperature and about 1500°C , whereby heating oven contamination in the form of peeled heating element oxide layer particles in a heating oven containing the heating element is prevented.

1734

Claim 2 (previously presented): A method according to Claim 1, wherein the SiO_2 present in the mixture is a silicate and does not affect molybdenum silicide crystal lattice symmetry.

Claim 3 (canceled)

Claim 4 (previously presented): A method according to Claim 1, wherein x lies in the range of 0.45 - 0.55.

Claim 5 (previously presented): A method according to Claim 1, including the step of partially substituting at least one of Re and W in the material $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ for molybdenum.

Claim 6 (currently amended): An electrical heating element that is substantially ~~of the~~ molybdenum silicide ~~type~~ and alloys of that material, said element consisting essentially of the materials $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 , wherein x lies in the range of 0.4 - 0.6; wherein SiO_2 having a purity of at least 98% is included in the material for replacing bentonite clay in molybdenum silicide heating element compositions containing bentonite clay; and wherein the heating element includes on its surface ~~a protective~~ an oxide layer consisting essentially of Al_2O_3 that which oxide layer does not peel from the surface of the heating element under thermal cycling of the heating element between room temperature and about 1500°C , whereby heating oven contamination in the form of peeled

1734

heating element oxide layer particles in a heating oven containing the heating element is prevented.

Claim 7 (canceled)

Claim 8 (previously presented): A heating element according to Claim 6, wherein x lies in the range of 0.45 - 0.55.

Claim 9 (previously presented): A heating element according to Claim 6, wherein molybdenum in the material $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ is partially replaced with at least one of Re and W.

Claim 10 (previously presented): A method according to claim 2, wherein the silicate is mullite.

Claim 11 (previously presented): A method according to claim 2, wherein the silicate is sillimanite.